

# Introduction to Road Materials Engineering

Part 1: Components, Soils, Aggregates, Road Construction

Presented by SARF

Presenter:  
Ron Berkers




INTRODUCTION TO ROAD MATERIALS ENGINEERING

*Main aims of this course:*


To achieve a **PRACTICAL** understanding of **WHERE**, **WHY**, and **HOW** the different types and qualities of materials are used in road construction

## INTRODUCTION TO ROAD PAVEMENTS



3

## Typical road pavement structure



4

## Pavement types

### Flexible pavements

Well-graded crushed stone base



Water-bound macadam base



5

## Pavement types

### Flexible pavements

Hot-mixed asphalt base



Stabilized base




6

# Pavement types


## Rigid pavements

Jointed concrete (JCP)

Continuously reinforced concrete (CRCP)



Dowelled jointed concrete (Dowelled JCP)



7

# Pavement types

## Segmented block pavements





8




## Where does soil come from?

The Rock Cycle:



## Rock Cycle




<https://www.youtube.com/watch?v=EGK1KkJdQY>

11

### INTRODUCTION TO ROAD PAVEMENTS

#### Igneous Rock:

**Basalt:**



**Porphyry:**




**Granite:**



12

## Types of Igneous Rock



<https://www.youtube.com/watch?v=PrN7jygu4cQ>

13

## INTRODUCTION TO ROAD PAVEMENTS

### Sedimentary Rock:

**Sand Stone:**



**Shale:**




**Dolomite:**



14

## Sedimentary Rock types



<https://www.youtube.com/watch?v=uozyWZ6XQzM>

15

## INTRODUCTION TO ROAD PAVEMENTS

### Metamorphic Rock:

**Marble:**



**From Limestone or Dolomite**

**Slate:**



**From Shale**

**Quartzite:**



**From sandstone**

16

# Metamorphic Rock types

Scheme for Metamorphic Rock Identification

TEXTURE	GRAIN SIZE	COMPOSITION	TYPE OF METAMORPHISM	COMMENTS	ROCK NAME	MAP SYMBOL
FOLIATED MINERAL ALIGNMENT	Fine	MICA QUARTZ FELDSPAR AMPHIBOLE GARNET PYROXENE	Regional (Heat and pressure increase with depth) ↓	Low-grade metamorphism of shale	Slate	
	Fine to medium			Foliation surfaces shiny from microscopic mica crystals	Phyllite	
	Medium to coarse			Platy mica crystals visible from metamorphism of clay or feldspars	Schist	
	Medium to coarse			High-grade metamorphism; some mica changed to feldspar, segregated by mineral type into bands	Gneiss	
NONFOLIATED	Fine	Variable	Contact (Heat)	Various rocks changed by heat from nearby magma/lava	Hornfels	
	Fine to coarse	Quartz	Regional or Contact	Metamorphism of quartz sandstone	Quartzite	
	Coarse	Calcite and/or dolomite		Metamorphism of limestone or dolostone	Marble	
	Coarse	Various minerals in particles and matrix		Pebbles may be distorted or stretched	Metaconglomerate	

ShowMe.com

17

[https://www.youtube.com/watch?v=D4eG\\_8v4Rfk](https://www.youtube.com/watch?v=D4eG_8v4Rfk)

The most important properties of soils and aggregates

What do we mean by SOILS and AGGREGATES ?

## Typical soils profile



Top soil – humus enriched, fertile

Sandy or clayey soil, gravel – transported or residual

Weathered or fresh rock

Quality improves ↓

18

## What do we mean by SOILS and AGGREGATES ?


### Typical soils profile



19

## What do we mean by SOILS and AGGREGATES ?

### Typical soils profile



20



## *Most important properties of soils:*

- Grading
- Plasticity
- Strength


21

## Grading


(Particle size distribution)

### *Poorly graded materials*

Coarsely graded – large particle sizes



Finely graded – small particle sizes



***But both are poorly graded !***

*(poor particle distribution)*

22

# Grading

(Particle size distribution)

## Well graded materials

Good particle distribution –

The different sized particles “pack” into the available spaces


*Can be described as “continuously graded”*

Comparison with poorly graded materials:

- higher degree of compaction possible
- reduced permeability
- usually higher strengths


*Coarse well graded – large maximum size*

*Fine well grade – small maximum size*



23

# Grading



*Nest of sieves*

S  
m  
a  
l  
l  
e  
r  
  
S  
i  
z  
e  
s




24


## INDICATOR TESTS

### GRADING ANALYSIS

Classification  
according to  
particle size




25



26

## INDICATOR TESTS


### ATTERBERG LIMITS



27



Liquid limit device – used to determine liquid limit



Linear shrinkage trough  
– used to determine  
linear shrinkage


28

## INDICATOR TESTS

### LINEAR SHRINKAGE

LS = Linear Shrinkage of the soil fines  
from the Liquid Limit test in a metal  
trough on drying


Provides a useful check of plasticity and  
moisture sensitivity  
(2 x LS = roughly PI)



*GRADING, PI and LS can with experience  
and knowledge of the soil type provide a  
very good preliminary guide to the  
engineering properties of a soil*


29

### Indication of quality based on plasticity index (PI)



30


## Moisture/density relationship



31

## Moisture/density relationship

### Modified AASHTO Maximum Dry Density Test [TMH1 – A7] Revised SANS 3001-GR30



Uses standard mould, rammer, drop, number of layers and blows

To provide a STANDARD COMPACTIVE EFFORT



The material is prepared by screening on a 19mm sieve, the oversize material is lightly crushed and added back into the sample

5 samples are compacted at a range of moisture contents

32




The most important properties of soils and aggregates




33

The most important properties of soils and aggregates



The OMC decreases with increases in compactive effort

34



35

## RELATIVE COMPACTION


When the actual density obtained is compared to the **Standard Density** the result, in percent, is termed the **Relative Compaction**

For Example:-


$$\text{Field Density} = 1985 \text{ kg/m}^3$$

$$\text{MDD} = 2120 \text{ kg/m}^3$$

$$\text{Relative Compaction (MDD)} = 1985 \div 2120 \times 100 = \mathbf{93.6\%}$$



*Maximum density*



**=**

**RELATIVE COMPACTION**


36

## CALIFORNIA BEARING RATIO (CBR)


### CRUDE TEST OF (BEARING) STENGTH

- Samples prepared at **MDD OMC** using three compactive efforts which give: 100%, about 96% and 93% Relative Compaction
- After soaking, a **standard** plunger (2ins Diam) is forced into the sample and the resisting force is measured at 2,5mm, 5mm and 7,5mm penetration
- The resisting force is divided by the **Standard Force** (OJ Porter) to give the CBR


Prepare 3 moulds at OMC using different compaction efforts



Soak in water bath for 4 days, measure "SWELL"




Penetrate in press, measuring resisting force at depths of 2.5mm, 5mm and 7.5mm



37

### Indication of quality based on CBR value




38

The most important properties of soils and aggregates

TRH 14 : 1985 Guidelines for road construction materials

Properties of untreated materials



Type	Summary of Requirements	
Graded crushed stone	G1	Crushed from solid good <b>rock</b> . Strict grading requirement. <b>Non-parent fines disallowed</b> . High degree of compaction specified – typically 89% ARD. LL max 25, PI max 4, LS max 4, ACV max 29%, 10% FACT min 110 kN
	G2 & G3	Crushed from <b>rock, boulders, or coarse gravel</b> . Strict grading requirement. <b>May include non-parent fines</b> . LL max 25, PI max 6, LS max 3. CBR ≥ 80, Swell max 0.2%
Natural gravels	G4	<b>Natural gravel</b> that may require crushing. Grading specified. <b>May contain non-parent fines</b> . LL max 25, PI max 6, LS max 3. CBR ≥ 80, Swell max 0.2%
	G5	Natural gravel that may require crushing. LL max 30, PI max 10, LS max 5, CBR ≥ 45, Swell max 0.5%
	G6	PI ≥ 12 or 3GM+10. CBR ≥ 25 at 93% compaction. Swell max 1.0%
Gravel - soils	G7	PI ≥ 12 or 3GM+10. CBR ≥ 15 at 93% compaction. Swell max 1.5%
	G8	CBR ≥ 10 at 90% compaction. Swell max 1.5%
	G9	CBR ≥ 7 at 90% compaction. Swell max 1.5%
	G10	CBR ≥ 3 at 90% compaction. Swell max 1.5%

*Note: Some additional requirements in COLTO*

39

The most important properties of soils and aggregates

Problem materials

Type	Situation	Remedy
Soft soils	Vlei and estuarine. Prone to settlement	Investigate extent to decide most practical treatment. Consider: <ul style="list-style-type: none"> <li>• remove and replace</li> <li>• install subsoil drainage</li> <li>• install geofabrics</li> <li>• treat (stabilize) with lime</li> </ul>
Expansive clays	Use PI and clay component with van der Merwe activity chart. Usually: LL > 30, PI >12, LS >8	Investigate extent to decide most practical treatment. Consider: <ul style="list-style-type: none"> <li>• remove and replace at least 600mm with stable material</li> <li>• stabilize with lime</li> <li>• employ methods to keep moisture content stable</li> </ul>
Collapsible soils	Typically low density sandy materials which densify at high moisture contents.	Consider impact rolling or ripping and recompacting to at least 600mm
Dispersive soils	Soils form dongas, gullies and tunnels. Contain sodium or lithium ions	Minimum use of these materials in fills. Consider: <ul style="list-style-type: none"> <li>• removal to depth of at least 600mm</li> <li>• treat with gypsum</li> </ul>

40

## Aggregates

Typical sieve sizes

Sieve Size (mm)	Class.
37.5	C
28.	O
20.	A
14	R
10	S
7	E
5	
2	F
1	I
0.600	N
0.300	E
0.150	
0.075	Filler

Single sized aggregates for surfacing

Sieve Size (mm)	20 Nominal size	14 Nominal size	10 Nominal size	7 Nominal size
37.5				
28	100			
20	85-100	100		
14	0-30	85-100	100	
10	0-5	0-30	85-100	100
7		0-5	0-30	85-100
5			0-5	0-30
2				0-5
1				
0.600				
0.300				
0.150				
0.075				

The nominal maximum particle size (NMPS) is the one sieve size larger than the largest sieve to retain a minimum of 15 percent of the aggregate particles

41

## Aggregates

Most important properties:


■ Grading



■ Shape



■ Strength




■ Durability



42

## Aggregate Strength Tests



## AGGREGATE STRENGTH

- ✓ Treton Test - Impact Resistance on -20mm +16mm stone
- ✓ Aggregate Crushing Value (ACV) and 10%FACT : (SANS 3001 – AG10), wet and dry on -14mm + 10mm stone – Crushing Resistance
- ✓ Modified Ball-Mill Test, (SANS 3001 – AG16) wet and dry, on whole sample - Resistance to degradation during construction and during pavement life

44



## Basic compaction technology



### STATIC ROLLER

Used mostly for compacting hot-mixed asphalt and in the construction of chip seals. Some road authorities prefer to use it for compacting water-bound macadam.



### SMOOTH DRUM VIBRATING ROLLER

Extensively used for the compaction of rock-fill and soils in the construction of earthworks as well as the granular pavement layerworks.



### PADFOOT VIBRATING ROLLER

Used extensively for compaction in the construction of earthworks and lower pavement layerworks. Breaks down soft rock such as mudstone and shale.



### DOUBLE DRUM VIBRATING ROLLER

Compaction of hot-mixed asphalt


### PNEUMATIC (RUBBER) TYRED ROLLER

Compaction of hot-mixed asphalt, as well as in the construction of chip seals



## Basic compaction technology

### Main forms of compaction





## Impact rollers

Used for compaction of earthworks. Useful in dry regions and for compaction of collapsible materials




*Impact rollers may be 4 or 5 sided*




47

## PRINCIPLES OF VIBRATORY COMPACTION




*Static compaction*



*Vibratory compaction*


48

## Principles of vibration rollers



## Important criteria for vibratory rollers


### Static linear load




*Static linear load = drum axle load ÷ drum width*

### Vibrating mass

Higher vibrating mass = higher compaction performance



## Vibratory roller settings for rockfill, soils and gravels



1. Start the compaction using *HIGH AMPLITUDE / LOW FREQUENCY* setting




2. Complete the compaction using *LOW AMPLITUDE / HIGH FREQUENCY* setting




51

## PRINCIPLES OF VIBRATORY COMPACTION




*Compaction starts at bottom of layer*

*High amplitude setting*




52

## PRINCIPLES OF VIBRATORY COMPACTION



53

## PRINCIPLES OF VIBRATORY COMPACTION




*The result:*

*The full thickness of the layer is properly compacted*

54

## Effect of rolling speed on compaction



The number of vibration impacts decreases as speed increases causing reduction in compaction – required more passes to achieved same level of compaction

### TYPICAL OPTIMUM ROLLER SPEEDS

Rockfill	1 – 2.5 km/h
Gravel, sand	2 – 4 km/h


55

## Measurement of compaction


### *Nuclear gauge*



Back scatter



Direct transmission



56



## Measurement of compaction


### *Sand replacement*

Place the density ring on the pavement surface and bed it in

Seat the density funnel in the ring

Pour the calibrated, weighed sand into the density funnel. Close the tap once the sand has stopped running in

Pour the sand in the top of the density funnel back into the container




57

## Measurement of compaction

### *Sand replacement*

Remove material from the compacted layer using a chisel

Place the material in an airtight container




58

## Measurement of compaction

### *Sand replacement*


Once the hole is complete, refit the density funnel to the ring

Pour in the calibrated, weighed sand into the funnel until it stops running in. Close the tap and transfer the sand from the top of the funnel into the container





59


## Road construction



60



## Roadbed preparation



63

## Roadbed preparation



64

## Roadbed preparation

*Replace with granular material*



Compact the roadbed using a vibrating tamper roller – ensure that the roadbed is stable without signs of “heaving”

*Normally minimum 90% Modified AASHTO compaction required*



65

## Fill construction

Compacted layer thickness  $\leq 200$  mm, except for rockfill

Minimum G10 quality




*Normally compaction is minimum 90% Modified AASHTO*

66

## Selected layers

Minimum G7 quality, compacted to min. 93% Mod. AASHTO



Minimum G9 quality, compacted to min. 93% Mod. AASHTO

*The thickness of the selected layers are normally 150 mm*

67

## Subbase

### Granular pavement types

- G5 or G6 (for lighter pavement designs)

### Stabilised subbase pavement types

- C3 or C4 (usually heavier pavement designs)



*The subbase layer is compacted to 95% to 98% Modified AASHTO depending upon the pavement design*

68

## Base Flexible pavements

### Well-graded crushed stone base

G1 – very high quality, well-graded crushed stone, compacted to min. 89% ARD

G2 – high quality, well graded crushed stone, compacted to min. 85% BRD



### Water-bound macadam base

WB – high quality, large, single sized crushed stone, with finely graded, clean crusher dust vibrated into voids. Usually constructed and compacted in accordance to method specification



## Base Flexible pavements

### Hot-mixed asphalt base

Normally continuously graded mix. Usually reserved for heavier pavement designs



### Stabilised base

Normally restricted to lighter pavement designs in areas where other pavement designs are not feasible. Prone to block cracking

